

## Style 700

### MATERIAL PROPERTIES\*:

<b>Color:</b>	Green
<b>Composition:</b>	Aramid & inorganic fibers with nitrile binder
<b>Fluid Services</b> (see chemical resistance guide):	Water, aliphatic hydrocarbons, oils and gasoline
<b>Temperature<sup>1</sup>, °F (°C)</b>	
Minimum:	-100 (-73)
Continuous Max:	+400 (+205)
Maximum:	+700 (+370)
<b>Pressure<sup>1</sup>, Maximum, psig (bar):</b>	1000 (70)
<b>P x T (max.)<sup>1</sup>, psig x °F (bar x °C):</b>	
1/32 and 1/16":	350,000 (12,000)
1/8"	250,000 (8,600)

### TYPICAL PHYSICAL PROPERTIES\*:

<b>ASTM F36</b>	<b>Compressibility</b> , average, %:	8
<b>ASTM F36</b>	<b>Recovery</b> , %:	50
<b>ASTM F38</b>	<b>Creep Relaxation</b> , %:	25
<b>ASTM F152</b>	<b>Tensile</b> , Across Grain, psi (N/mm <sup>2</sup> ):	1500 (10.3)
<b>ASTM F1315</b>	<b>Density</b> , lbs./ft. <sup>3</sup> (grams/cm <sup>3</sup> ):	120 (1.9)
<b>ASTM F433</b>	<b>Thermal Conductivity (K)</b> , W/m <sup>2</sup> K (Btu.in./hr.ft. <sup>2</sup> .°F):	0.29-0.38 (2.00-2.65)
<b>ASTM D149</b>	<b>Dielectric Properties</b> , range, volts/mil.	
	Sample conditioning	<u>1/32"</u> <u>1/8"</u>
	3 hours at 250°F	597 290
	96 hours at 100% Relative Humidity:	<2 <2
<b>ASTM F586</b>	<b>Design Factors</b>	<u>1/16" &amp; Under</u> <u>1/8"</u>
	"m" factor:	4.0 <sup>(3)</sup> 4.0 <sup>(4)</sup>
	"y" factor, psi (N/mm <sup>2</sup> ):	2500 (17.2) <sup>(3)</sup> 2500 (17.2) <sup>(4)</sup>

### SEALING CHARACTERISTICS\*

	ASTM F37B – Fuel A	ASTM F37B - Nitrogen
<b>Gasket Load</b> , psi (N/mm <sup>2</sup> ):	500 (3.5)	3000 (20.7)
<b>Internal Pressure</b> , psig (bar):	9.8 (0.7)	30 (2)
<b>Leakage</b>	<b>1.0 ml/hr</b>	<b>2.0 ml/hr</b>

#### Notes:

\* This is a general guide and should not be the sole means of selecting or rejecting this material. ASTM test results in accordance with ASTM F-104; properties

<sup>1</sup> Based on ANSI RF flanges at our preferred torque. When approaching maximum pressure, continuous operating temperature, minimum temperature or 50% of maximum PxT, consult Garlock Applications Engineering. Minimum temperature rating is conservative.

<sup>3</sup> Actual tests showed 3.7 and 1200 psi. These are considered too low for effective flange design.

<sup>4</sup> Actual tests showed 3.6 and 1150 psi. These are considered too low for effective flange design.