

STYLE 5450

Style 5450 is 100% glass fiber braid, supplied dry - but is also available with a graphite finish upon request.

Style 5450 is usually found on static sealing or gasketing services, and sometimes for reciprocating motions. It's useful for furnace door seals, coke oven door jam seals, sealing strainer in distillation columns, and gasketing around doors of wood-burning stoves (may require rope).

Style 5450 resists organic solvents, most acids, and mild alkalis. It has higher heat resistance, does not burn or smolder, is dimensionally stable, has excellent electrical properties, is soft and flexible, has excellent insulating characteristics and retains it's strength at high temperatures.

Style 5450 has been accepted as a substitute for asbestos packing materials by MSHA - Acceptance Number 101983GI. This product complies with all the requirements of Title 30, CFR, Chapter I, Part II, Appendix II (figures 8, 9, and 10) regarding compression, flammability, and explosion.

TEMPERATURE:	To +1000°F(+538°C)
PH RANGE:	2 – 11
PRESSURE:	10 psi (1 Bar) Static
CONSTRUCTION:	LATTICE BRAID® Sizes 3/8" - 2" available