



an EnPro Industries family of companies

# Klozure Material Properties

## MATERIAL PROPERTIES FOR KLOZURE® OIL SEALS

Material	Color	Coefficient of Friction	Operating Temp.	Max Spike Temp.	Abrasion Resistance	Chemical Resistance
Mill-Right® N	Black	1.788	-40°F to 200°F (-40°C to 93°C)	250°F (123°C)	Moderate	Moderate
Mill-Right® ES	Blue	1.053	-40°F to 300°F (-40°C to 148°C)	350°F (177°C)	High	Improved
Mill-Right® V	Green	1.158	-22°F to 400°F (-30°C to 204°C)	450°F (232°C)	High	Very Good
Silicone	Light Blue (FDA - Red)	2.000+	-75°F to 350°F (-59°C to 176°C)	400°F (204°C)	Low	Very Good
Gylon	Black (FDA - White)	0.1	-120°F to 400°F (-84°C to 204°C)	450°F (232°C)	High	Excellent